

## NZAC00214 Dulux Acratex 958 AcraSand

### Introduction

Part A  
194-51943

### Description and Image

DULUX AcraTex 958 AcraSand is an extremely tough 100% pure acrylic high build coating, especially formulated to produce a granular, near flat, appearance very much like that of fine granular sandstone in two coats..

### Features and Benefits

- Water based
- Easy to texture
- Versatile application
- 10 year warranty
- Easy, safe and economical clean-up.
- Range of texture profiles possible.
- Quick, efficient application with roller, spray and trowel.
- Guaranteed long term exterior durability.

### Uses

DULUX AcraTex 958 AcraSand can be used where extreme high performance is required and where a more natural granular appearance is aesthetically desired. Its mid build rheology will cover small holes and fine hairline cracks in a single fast applying and economical coat on all masonry substrates. It should be overcoated with DULUX AcraTex AcraShield Advance to give true colour consistency



### Performance Guide

Salt  
**Resists salt spray especially when topcoated with DULUX AcraTex AcraShield Advance**

Heat Resistance  
**Up to 90C (dry).**

Solvent  
**Resists alcohol and aliphatic hydrocarbons. Sensitive to strong solvents.**

Abrasion  
**Good abrasion resistance especially when topcoated with DULUX AcraTex AcraShield Advance**

Typical Properties			
V.O.C. Content <b>&lt;75 g/L</b>			
Application Methods			
 <b>Brush</b>  <b>Roller</b>			
Specifications	Solids by Volume		
	<input type="text" value="50"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="250"/>	<input type="text" value="330"/>	<input type="text" value="250"/>
Dry Film Per Coat (microns)	<input type="text" value="125"/>	<input type="text" value="165"/>	<input type="text" value="125"/>
Theoretical Spread Rate (m <sup>2</sup> /L)	<input type="text" value="4"/>	<input type="text" value="3.03"/>	<input type="text" value="4"/>
Drying Time			
	Min	Max	Recommended
Recoat Time (min/hours)	<input type="text" value="24 hours"/>	<input type="text" value="Indefinite"/>	<input type="text"/>

Application Guide
<p>Surface Preparation</p> <p>All surfaces must be cured, clean, sound and free of all contaminants such as form oils, release agents and mortar splashes. Surface imperfections, misalignments and protrusions must be levelled, patched and completely flush to surrounding surfaces. Metal tie wires, etc on surface must be removed and treated against corrosion. Prime substrate with DULUX AcraPrimer 501/8 HAR Primer or surfaces of powdery nature will require consolidation with DULUX AcraTex AcraPrime 501/2. If using DULUX AcraPrime 501/8 HAR primer, ensure alkaline surfaces have aged (a minimum of 7 days curing, possibly longer depending on conditions). If using a different primer ensure alkaline surfaces have aged for 28 days minimum.</p>
<p>Application Procedure and Equipment</p> <p>Brush and roller Refer to the Dulux AcraTex Applicators Training Manual for detailed instructions. A minimum of two coats is required (minimum DFT of 125 micrometres) to avoid "holidays" in the coating.</p>

Health and Safety	
SDS Number <b>14557369</b>	SDS Link <a href="#">View SDS Link</a>
Using Safety Precautions For detailed information refer to the current Material Safety Data sheet available through Dulux NZ Sales and Customer Service Offices.	
<b>Please refer to SDS Link. In case of emergency, please call 0800 220 770.</b>	

**Precautions and Limitations**

A DULUX warranty will be provided confirming protection against flaking & peeling for a period of seven years when the full DULUX AcraTex system is applied by a DULUX trained applicator, according to specification, & at the specified spreading rates, & to the surface preparation details described in the AcraTex Specification Manual.  
DULUX AcraTex Acra-Sand must only be applied in air temperatures between 10C and 30C and must be protected from rain and frost for the first 24 hours. Avoid application in full sun or hot, windy conditions.

**Transport and Storage**

Line Shade /Pack A <b>194-51943</b>	Shipment Name <b>Not dangerous goods.No special transport requirements.</b>
Size: <b>15 litre</b>	Weight: <b>23 kg</b>

**Disclaimer**

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from [www.duspecplus.co.nz](http://www.duspecplus.co.nz). Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.